



DayStrong Rubber Products  
 11 Forrester Drive  
 PO Box 781  
 Mauldin, South Carolina 29662  
 Phone 864-284-1052

## RIBBON TYPE ROLL COVERING SPECIFICATIONS and TECHNICAL DATA

DayStrong Compound Number	DK107	DK154 & DK153	G310E Embossed	G530E Embossed	SF 150	G320	G520
<b>Compound</b>	<b>Cork &amp; Rubber</b>	<b>Cork &amp; Rubber</b>	<b>Nitrile Rubber</b>	<b>Natural Rubber</b>	<b>Nitrile Rubber</b>	<b>Nitrile Rubber</b>	<b>Carboxylated Nitrile</b>
<b>Surface Finish</b>	<b>Smooth</b>	<b>Smooth</b>	<b>Embossed</b>	<b>Embossed</b>	<b>Sand Finish</b>	<b>Sand Finish</b>	<b>Sand Finish</b>
Color	Tan	Black	Dark Blue	Tan	Orange	Blue	White
Shore A	45+/-10	45+/-10	65+/-5	45+/-5	60+/-5	65+/-5	75+/-5
Backing	Cotton/Poly	Cotton	Cotton/Poly	Cotton	Cotton	Cotton/Poly	Cotton/Poly
Thickness MM	^All Thickness +/- 0.25	^0.8mm -0/+0.25mm 1.98mm +/- 0.13mm All Others +/- 0.25mm	2.30 +/- 0.25	1.90 +/- 0.25	1.90 +/- 0.25	2.20 +/- 0.25	2.40 +/- 0.25
Thickness Imperial	^All Thickness +/- .010	^0.031" -0/+0.010 .075" +/- .005 All Others +/- .010	.090 +/- .010	.075 +/- .010	.075 +/- .010	.085 +/- .010	.095 +/- .010
Maximum Operating Temperature C/F for Material. Type of Adhesive Used May Reduce Maximum Operating Temp.	104/220	104/220	121/250	104/220	121/250	121/250	121/250
Abrasion Resistance Rank*	N/A	N/A	2	1	3	2	1
Surface Friction Rank*	N/A	N/A	2	1	1	1	2
Fiber Finish Resistance Rank*	N/A	N/A	1	3	1	1	1
Additional Information	^ available in .0625"/1.6mm & .125"/3.2mm	^ available in .031"/0.8mm, .0625"/1.6mm, .075"/1.98mm, .094"/2.4mm & .125"/3.2mm	available with pressure sensitive adhesive	available with pressure sensitive adhesive minimum order quantity may apply	available with pressure sensitive adhesive	available with pressure sensitive adhesive	available with pressure sensitive adhesive

DayStrong Compound Number	NO732	BR14	G310	G530	G550	G330	G540
<b>Compound</b>	<b>Nitrile Rubber</b>	<b>PVC</b>	<b>Nitrile Rubber</b>	<b>Natural Rubber</b>	<b>Nitrile Rubber</b>	<b>Carboxylated Nitrile</b>	<b>Natural Rubber</b>
<b>Surface Finish</b>	<b>Smooth</b>	<b>Smooth</b>	<b>Smooth</b>	<b>Smooth</b>	<b>Rough Top</b>	<b>Rough Top</b>	<b>Rough Top</b>
Color	Gray	Light Blue	Dark Blue	Tan	Gray	Gray/Yellow	Tan
Shore A	42+/-5	72+/-5	65+/-5	45+/-5	55+/-5	65+/-5	39+/-5
Backing	Cotton	Cotton/Poly	Cotton/Poly	Cotton/Poly	Cotton/Poly	Cotton/Poly	Cotton/Poly
Thickness MM	2.10 +/- .025	2.10 +/- 0.25	2.30 +/- 0.25	1.90 +/- 0.25	3.90 +/- 0.50	4.90 +/- 0.50	4.80 +/- 0.50
Thickness Imperial	.083 +/- .010	.083 +/- .010	.090 +/- .010	.075 +/- .010	.155 +/- .020	.195 +/- .020	.190 +/- .020
Maximum Operating Temperature C/F for Material. Type of Adhesive Used May Reduce Maximum Operating Temp.	93/200	90/194	121/250	104/220	121/250	121/250	104/220
Abrasion Resistance Rank*	3	2	2	1	2	1	1
Surface Friction Rank*	2	2	2	1	2	2	1
Fiber Finish Resistance Rank*	1	2	1	3	1	1	2
Additional Information	available with pressure sensitive adhesive		available with pressure sensitive adhesive	available with pressure sensitive adhesive minimum order quantity may apply	available with pressure sensitive adhesive	available with pressure sensitive adhesive	available with pressure sensitive adhesive minimum order quantity may apply

\* Rank within surface finish category based on laboratory testing